

WHAT IS CLAIMED IS:

1. A tearable film made of plastic material, for flexible packagings, comprising a plastic polymer material that is extruded with flat-die or blown-film technologies and 1 to 50% by weight of an addition substance of
5 inorganic material in powder form.

2. The film of claim 1, wherein said plastic polymer is selected from a group comprising polypropylene and polyethylene.

3. The film of claim 1, wherein said inorganic material is selected from a group comprising talc, calcium carbonate and kaolin.

10 4. The film of claim 1, wherein said addition substance is approximately 3-5% by weight.

5. The film of claim 1, laminated with a further film selected among films made of plastic materials and aluminum foil.

6. The film of claim 1, wherein the inorganic material constitutes an
15 inorganic filler, the film being a three-layer coextruded film in which the inorganic filler is confined to a central layer thereof.

7. The film of claim 1, wherein the inorganic material constitutes an inorganic filler, the film being a two-layer coextruded film in which the inorganic filler is confined to only one of the film layers.